



AMENDMENTS TO THE CLAIMS

1. **(Currently amended)** A method for electrolytic coating of a material with an aluminum, magnesium or alloys of aluminum and magnesium, said method comprising

immersing ~~the~~ an aluminum/magnesium alloy or zinc/magnesium alloy material in ~~an~~ a halogen-free electrolytic bath comprising electrolyte for pretreatment, wherein said material is electrically connected as an anode therein, and anodically charging the material, and

reversing polarity of the material, thereby

performing the electrolytic coating in the same electrolyte immediately thereafter, the electrolytic bath further comprising organoaluminum compounds of general formulas (I) and (II)



as the electrolyte, wherein n is equal to 0 or 1, M is sodium or potassium, and R^1 , R^2 , R^3 , R^4 are the same or different, R^1 , R^2 , R^3 , R^4 being a C_1 - C_4 alkyl group, and a halogen-free, aprotic solvent being used as solvent for the electrolyte.

2. **(Previously presented)** The method according to claim 1, wherein a mixture of the complexes $K[AlEt_4]$, $Na[AlEt_4]$ and $AlEt_3$ is employed as the electrolyte.

3. **(Previously presented)** The method according to claim 2, wherein a molar ratio of said complexes $K[AlEt_4]$, $Na[AlEt_4]$ to $AlEt_3$ is from 1:0.5 to 1:3.

4. **(Currently amended)** The method according to claim 2, wherein 0 to 25 mole-%_[5] $Na[AlEt_4]$ is employed, relative to the mixture of the complexes $K[AlEt_4]$ and $Na[AlEt_4]$.

5. **(Currently amended)** The method according to Claim 2, wherein a mixture of 0.8 mol $K[AlEt_4]$, 0.2 mol $Na[AlEt_4]$, 2.0 mol $AlEt_3$ in 3.3 mol toluene is used as the electrolyte bath.

6. **(Previously presented)** The method according to claim 1, wherein a mixture of $Na[Et_3Al-H-AlEt_3]$ and $Na[AlEt_4]$ and $AlEt_3$ is used as the electrolyte.

7. **(Previously presented)** The method according to claim 6, wherein a molar ratio of $Na[Et_3Al-H-AlEt_3]$ to $Na[AlEt_4]$ is from 4:1 to 1:1.

Appl. No. : 10/528,125
Filed : November 21, 2005

8. **(Previously presented)** The method according to claim 7, wherein a molar ratio of $\text{Na}[\text{AlEt}_4]$ to AlEt_3 is 1:2.

9. **(Currently amended)** The method according to Claim 8, wherein a mixture of 1 mol $\text{Na}[\text{Et}_3\text{Al-H-AlEt}_3]$, 0.5 mol $\text{Na}[\text{AlEt}_4]$ and 1 mol AlEt_3 in 3 mol toluene is used as the electrolyte bath.

10. **(Previously presented)** The method according to Claim 1 wherein the electrolytic coating is performed at temperatures of from 80 to 105°C.

11. **(Previously presented)** The method according to Claim 1 wherein the pretreatment is performed for a period of from 1 to 20 minutes.

12. **(Previously presented)** The method according to Claim 1, wherein the pretreatment is performed at an anodic load of the material with a current density of from 0.2 to 2 A/dm^2 .

13. **(Previously presented)** The method of Claim 3, wherein the molar ratio of said complexes $\text{K}[\text{AlEt}_4]$, $\text{Na}[\text{AlEt}_4]$ to AlEt_3 is 1:2.

14. **(Previously presented)** The method according to claim 4 wherein 5 to 20 mole-% $\text{Na}[\text{AlEt}_4]$ is employed, relative to the mixture of the complexes $\text{K}[\text{AlEt}_4]$ and $\text{Na}[\text{AlEt}_4]$.

15. **(Previously presented)** The method of Claim 7, wherein the molar ratio of $\text{Na}[\text{Et}_3\text{Al-H-AlEt}_3]$ to $\text{Na}[\text{AlEt}_4]$ is 2:1.

16. **(Previously presented)** The method of Claim 10, wherein the electrolytic coating is performed at temperatures of from 91 to 100°C.

17. **(Previously presented)** The method of Claim 11, wherein the pretreatment is performed for a period of from 5 to 15 minutes.

18. **(Previously presented)** The method of Claim 12, wherein the pretreatment is performed at an anodic load of the material with a current density of from 0.5 to 1.5 A/dm^2 .